



CALIFORNIA SCIENCE & ENGINEERING FAIR 2018 PROJECT SUMMARY

Name(s) Laura Noronha	Project Number S0619
Project Title TiO₂ Hollow Shell around Gold Nanoparticles: A More Efficient Photocatalyst	
<p style="text-align: center;">Abstract</p> <p>Objectives/Goals Synthesize gold nanoparticles surrounded by a TiO₂ hollow shell to serve as a more efficient photocatalyst.</p> <p>Methods/Materials First, the gold nanoparticles were prepared by mixing the prepared gold precursor with trisodium citrate. Then, polyvinylpyrrolidone (PVP) was coated on the gold nanoparticles to prevent them from aggregating. The nanoparticles were then coated with a layer of silica. The titania was coated over the silica, and the silica was then etched, which created a hollow space around the gold nanoparticles. Hydrochloric acid (HCl) was added so that the TiO₂ surrounding shell would remain intact under high temperature conditions during calcination. Titania hollow shells without a gold core were synthesized as a control. The TiO₂ and the gold-nanoparticles with TiO₂ were then compared to see which of the two would be a more efficient photocatalyst in the degradation of the organic dye Rhodamine B (RhB). The 3 samples analyzed were: RhB blank sample, RhB with only TiO₂ hollow shell, and RhB with Au@TiO₂ catalyst. 1 mL of each sample was taken every 10 minutes for one hour. The UV-visible absorption spectrophotometer was used to compare breakdown rates of the RhB in each of the 3 samples.</p> <p>Results The RhB decomposed the slowest with no catalyst. When the TiO₂ shell was sonicated in the sample, the RhB degraded at a much faster rate. The reaction worked the best with the Au@TiO₂ photocatalyst, especially with the samples taken from thirty minutes to sixty minutes. At ten minutes, the TiO₂ had a slightly more efficient breakdown, but the gold and titania quickly surpassed the rate of the reaction using only titania.</p> <p>Conclusions/Discussion Using gold nanoparticles in a TiO₂ shell is a more efficient photocatalyst. This is due to the surface plasmon resonance property of gold nanoparticles which causes them to absorb and scatter light. This in turn optimizes the excitation of electrons in the titania hollow shell, leading to the formation of more electron hole pairs. Formation of electron hole pairs serves as the basis for the photocatalytic activity of titania. This can be used in many reactions such as decomposition of organic dyes and redox reactions including the splitting of water to produce hydrogen gas. It is a possible solution for a cleaner source of hydrogen gas.</p>	
Summary Statement Optimal photocatalytic activity was achieved by combining a gold nanoparticle inside a titania hollow shell.	
Help Received This project was completed at Dr. Yadong Yin's lab in the Department of Chemistry at the University of California Riverside. Graduate student Rashed Aleisa mentored me in this project.	